



PNEU-DRAULICS

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:

- 1 = Satisfactory
- 2 = Fair (Usually OK for Static Seal)
- 3 = Doubtful (Sometimes OK for Static Seal)
- 4 = Unsatisfactory
- X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
1-Butene 2-Ethyl	1	4	1	4	4	1	4	4	4	4	4	4	3	4
1-Chloro 1-Nitro Ethane	4	4	4	4	4	4	4	4	4	4	4	4	4	4
AN-O-3 Grade M	1	4	1	2	4	1	1	4	4	4	4	2	1	2
AN-O-6	1	4	1	2	4	1	1	4	4	4	4	2	1	4
AN-VV-O-366b Hydr. Fluid	1	4	1	2	4	2	2	4	4	4	4	2	1	4
ASTM Oil, No.1	1	4	1	1	4	1	1	4	4	4	4	2	1	1
ASTM Oil, No.2	1	4	1	2	4	1	2	4	4	4	4	4	1	4
ASTM Oil, No.3	1	4	1	4	4	1	2	4	4	4	4	4	1	3
ASTM Oil, No.4	2	4	1	4	4	2	4	4	4	4	4	4	2	4
ASTM Reference Fuel A	1	4	1	2	4	2	1	4	4	4	4	2	1	4
ASTM Reference Fuel B	1	4	1	4	4	4	2	4	4	4	4	4	1	4
ASTM Reference Fuel C	2	4	1	4	4	4	4	4	4	4	4	4	2	4
ATL-857	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Acetaldehyde	3	2	4	3	3	4	4	2	2	2	2	3	4	2
Acetamide	1	1	3	1	4	4	4	2	4	4	4	2	1	2
Acetic Acid, 5%	2	1	1	1	2	4	4	1	2	2	2	1	2	1
Acetic Acid, Glacial	2	2	4	4	2	4	4	2	2	2	2	3	4	2
Acetic Acid, Hot, High Pressure	4	3	4	4	4	4	4	4	4	4	4	3	4	3
Acetic Anhydride	4	2	4	2	2	4	4	2	2	2	2	2	4	2
Acetone	4	1	4	4	4	4	4	1	4	4	4	3	4	4
Acetophenone	4	1	4	4	4	4	4	2	4	4	4	4	4	4
Acetyl Acetone	4	1	4	4	4	4	4	1	4	4	4	4	4	4
Acetyl Chloride	4	4	1	4	4	4	4	4	4	4	4	4	1	3
Acetylene	1	1	1	2	2	4	4	1	2	2	2	2	X	2
Acetylene Tetrabromide	4	1	1	2	4	X	4	1	X	X	X	X	X	X
Acrylonitrile	4	4	3	4	3	4	4	4	X	3	3	3	4	4
Aero Lubriplate	1	4	1	1	2	1	1	4	4	4	4	1	1	2
Aero Shell 17 Grease	1	4	1	2	4	1	1	4	4	4	4	1	1	2
Aero Shell 750	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Aero Shell 7A Grease	2	4	1	2	4	1	1	4	4	4	4	1	1	2
Aero Shell IAC	1	4	1	2	4	1	1	4	4	4	4	1	1	2
Aerosafe 2300	4	1	4	4	4	4	4	2	4	4	4	4	3	3
Aerosafe 2300W	4	1	4	4	4	4	4	2	4	4	4	4	3	3
Aerozene 50 (50% Hydrazine 50% UDMH)	3	1	4	4	4	X	4	1	4	4	4	4	4	4
Air Below 200° F	2	1	1	1	2	1	2	1	2	2	2	1	1	1
Air, 200 - 300° F	3	2	1	2	4	2	3	2	4	4	4	2	1	1
Air, 300 - 400° F	4	4	1	4	4	4	4	4	4	4	4	4	2	1
Air, 400 - 500° F	4	4	3	4	4	4	4	4	4	4	4	4	4	2
Alkazene	4	4	2	4	4	4	4	4	4	4	4	4	2	4
Aluminum Acetate	2	1	4	2	2	4	4	1	4	1	1	4	4	4
Aluminum Bromide	1	1	1	1	1	1	3	1	1	1	1	1	1	1
Aluminum Chloride	1	1	1	1	1	1	3	1	1	1	1	1	1	2
Aluminum Fluoride	1	1	1	1	1	X	3	1	1	1	2	1	1	2
Aluminum Nitrate	1	1	1	1	1	X	3	1	1	1	1	1	X	2
Aluminum Salts	1	1	1	1	1	1	3	1	1	1	1	1	1	1
Aluminum Sulphate	1	1	1	1	2	4	4	1	1	1	1	1	1	1
Alums-NH3 -Cr -K	1	1	4	1	1	4	X	1	1	1	1	1	1	4
Ambrex 33 (Mobil)	1	4	1	2	4	1	2	4	4	4	4	3	3	4
Ambrex 830 (Mobil)	1	3	1	2	4	1	1	3	4	4	4	2	1	2
Amines-Mixed	4	2	4	2	2	4	4	2	2	2	2	4	4	2
Ammonia and Lithium Metal in Solution	2	2	4	X	4	4	4	2	4	4	4	4	4	4
Ammonia, Gas, Cold	1	1	4	1	1	4	X	1	1	1	1	1	1	4
Ammonia, Gas, Hot	4	2	4	2	4	4	X	2	4	4	4	2	4	X
Ammonia, Liquid (Anhydrous)	2	1	4	1	4	4	4	1	4	4	4	2	4	2
Ammonium Carbonate	4	1	1	1	1	4	4	1	X	X	1	1	X	X
Ammonium Chloride, 2N	1	1	1	1	1	X	1	1	X	X	1	1	X	X
Ammonium Hydroxide, 3 Molar	1	1	3	1	2	4	4	1	2	2	2	1	1	1
Ammonium Hydroxide, Concentrated	4	1	4	1	3	4	4	1	3	3	3	1	1	1
Ammonium Nitrate, 2N	1	1	X	1	1	2	X	1	X	X	3	1	X	X
Ammonium Nitrite	1	1	X	1	1	X	X	1	1	1	1	1	X	2
Ammonium Persulfate 10%	4	1	X	1	4	4	4	1	X	1	1	X	X	X
Ammonium Persulfate Solution	4	1	X	X	4	4	4	1	X	1	1	X	X	X

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
 1 = Satisfactory
 2 = Fair (Usually OK for Static Seal)
 3 = Doubtful (Sometimes OK for Static Seal)
 4 = Unsatisfactory
 X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Ammonium Phosphate	1	1	4	1	1	X	X	1	X	1	1	1	X	1
Ammonium Phosphate, Dibasic	1	1	X	1	1	X	X	1	X	1	1	1	X	1
Ammonium Phosphate, Mono-Basic	1	1	X	1	1	X	X	1	X	1	1	1	X	1
Ammonium Phosphate, Tribasic	1	1	X	1	1	X	X	1	X	1	1	1	X	1
Ammonium Salts	1	1	3	1	1	3	X	1	X	1	1	1	3	1
Ammonium Sulfate	1	1	4	1	2	4	X	1	1	1	1	1	X	X
Ammonium Sulfide	1	1	4	1	2	4	X	1	1	1	1	1	X	X
Amyl Acetate	4	3	4	4	4	4	4	3	4	4	4	4	4	4
Amyl Alcohol	2	1	2	2	2	4	4	1	2	2	2	2	1	4
Amyl Borate	1	4	1	1	4	X	X	4	4	4	4	1	X	X
Amyl Chloride	X	4	1	4	4	4	X	4	4	4	4	4	4	4
Amyl Chloronaphthalene	4	4	1	4	4	4	X	4	4	4	4	4	2	4
Amyl Naphthalene	4	4	1	4	4	2	4	4	4	4	4	4	1	4
An-O-366	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Anderol, L- 826 (di-ester)	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Anderol, L- 829 (di-ester)	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Anderol, L-774 (di-ester)	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Ang-25 (Di-ester Base) (TG749)	2	4	1	4	4	2	4	4	4	4	4	4	2	2
Ang-25 (Glycerol Ester)	2	1	1	2	2	4	4	2	2	2	2	2	2	2
Anhydrous Ammonia	2	1	4	1	4	4	4	1	4	4	4	4	4	2
Anhydrous Hydrazine	4	2	4	2	1	4	4	2	4	4	4	2	4	X
Anhydrous Hydrogen Fluoride	4	1	4	X	4	4	X	1	4	4	4	X	4	X
Aniline	4	2	3	4	4	4	4	2	4	4	4	4	3	4
Aniline Dyes	4	2	2	2	2	4	4	2	2	2	2	2	2	3
Aniline Hydrochloride	2	2	2	4	3	4	4	2	4	2	2	4	2	3
Aniline Oil	4	2	3	4	4	4	4	2	4	4	4	4	3	4
Animal Oil (Lard Oil)	1	2	1	2	4	1	2	2	4	4	4	2	1	2
Ansul Ether 161 or 181	3	3	4	4	4	4	2	3	4	4	4	4	3	4
Argon	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Aroclor, 1248	3	2	1	4	4	4	4	2	4	4	4	4	2	2
Aroclor, 1254	4	2	1	4	4	4	4	4	4	4	4	4	2	3
Aroclor, 1260	1	X	1	1	1	4	4	1	1	1	1	1	1	1
Aromatic Fuel -50%	2	4	1	4	4	4	4	4	4	4	4	4	2	4
Arsenic Acid	1	1	1	1	1	3	3	1	1	1	2	1	1	1
Askarel	2	4	1	4	4	4	4	4	4	4	4	4	2	4
Asphalt	2	4	1	2	4	2	2	4	4	4	4	2	2	4
Atlantic Dominion F	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Atlantic Utro Gear-EP Lube.	1	4	1	2	4	1	1	4	4	4	4	4	1	4
Aure 903R (Mobil)	1	4	1	2	4	1	1	4	4	4	2	4	4	4
Automatic Transmission Fluid	1	4	1	2	4	1	2	4	4	4	4	3	X	4
Automotive Brake Fluid	3	1	4	2	1	4	4	2	X	X	X	2	4	3
Bardol B	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Barium Chloride	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Barium Hydroxide	1	1	1	1	1	4	4	1	1	1	1	1	1	1
Barium Salts	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Barium Sulfide	1	1	1	1	2	4	1	1	2	1	1	1	1	1
Bayol 35	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Bayol D	1	4	1	2	4	1	4	4	4	4	4	4	1	4
Beer	1	1	1	1	1	4	2	1	1	1	1	1	1	1
Beet Sugar Liquors	1	1	1	2	1	4	4	1	1	1	1	1	1	1
Benzaldehyde	4	1	4	4	4	4	4	1	4	4	4	1	4	2
Benzene	4	4	1	4	4	4	4	4	4	4	4	4	3	4
Benzenesulfonic Acid 10%	4	4	1	2	4	4	4	4	4	4	4	1	2	4
Benzochloride	4	1	1	4	4	4	X	2	4	4	4	4	1	X
Benzoic Acid	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Benzophenone	X	2	1	X	4	4	4	2	4	4	X	X	1	X
Benzyl Alcohol	4	2	1	2	4	4	4	2	4	4	4	2	2	2
Benzyl Benzoate	4	4	1	4	4	4	4	2	4	4	4	4	1	4
Benzyl Chloride	4	4	1	4	4	4	4	4	4	4	4	4	1	4
Black Point 77	1	1	1	3	3	3	3	1	3	3	3	3	3	3
Blast Furnace Gas	4	4	1	4	4	4	4	4	4	4	4	4	2	1
Bleach Liquor	3	1	1	2	3	4	4	1	2	2	3	1	2	2

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME



PNEU-DRAULICS

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:

- 1 = Satisfactory
- 2 = Fair (Usually OK for Static Seal)
- 3 = Doubtful (Sometimes OK for Static Seal)
- 4 = Unsatisfactory
- X = Insufficient Data

FLUID NAME	MATERIAL													
	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Borax	2	1	1	4	2	2	1	1	2	2	2	4	2	2
Bordeaux Mixture	2	1	1	2	2	4	4	1	2	2	2	1	2	2
Boric Acid	1	1	1	1	1	4	1	1	1	1	1	1	1	1
Boron Fluids (HEF)	2	4	1	4	4	4	4	4	4	4	4	4	2	4
Brake Fluid DOT3 (Glycol Type)	3	1	4	2	1	X	4	2	X	X	X	4	2	4
Bray GG-130	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Brayco 719-R (VV-H-910)	3	1	4	2	X	4	4	2	2	2	2	2	2	2
Brayco 885 (MIL-L-6085A)	2	4	1	4	4	2	1	4	4	4	4	4	2	4
Brayco 910	2	1	4	2	2	3	3	1	1	1	1	1	4	4
Bret 710	2	1	4	2	2	3	3	1	1	1	1	1	4	4
Brom - 113	3	4	X	4	4	X	X	4	X	X	X	4	X	4
Brom - 114	2	4	2	2	4	X	X	4	4	4	4	2	X	4
Bromine	4	4	1	4	4	4	4	4	4	4	4	4	4	4
Bromine Pentafluoride	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Bromine Trifluoride	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Bromine Water	4	2	1	4	4	4	4	4	4	4	4	1	2	4
Bromobenzene	4	4	1	4	4	4	4	4	4	4	4	4	1	4
Bromochloro Trifluoroethane	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Bunker Oil	1	4	1	4	4	1	2	4	4	4	4	4	1	2
Butadiene (Monomer)	4	4	1	4	4	4	4	4	4	4	4	4	1	4
Butane	1	4	1	1	3	1	1	4	4	4	4	2	3	4
Butane, 2, 2-Dimethyl	1	4	1	2	3	1	4	4	4	4	4	2	3	4
Butane, 2, 3-Dimethyl	1	4	1	2	3	1	4	4	4	4	4	2	3	4
Butanol (Butyl Alcohol)	1	2	1	1	1	4	4	2	1	1	1	1	1	2
Butter-Animal Fat	1	1	1	2	4	1	1	2	4	4	4	2	1	2
Butyl Acetyl Ricinoleate	2	1	1	2	4	X	4	1	4	4	4	2	2	X
Butyl Acrylate	4	4	4	4	4	X	4	4	4	4	4	4	4	X
Butyl Alcohol	1	2	1	1	1	4	4	2	1	1	1	1	1	2
Butyl Amine or N-Butyl Amine	3	3	4	4	4	4	4	4	4	4	4	4	4	4
Butyl Carbitol	4	1	3	3	4	4	X	1	4	4	4	2	4	4
Butyl Cellosolve	3	2	4	3	4	4	4	2	4	4	4	4	4	X
Butyl Cellosolve Adipate	4	2	2	4	4	4	4	2	4	4	4	4	2	2
Butyl Oleate	4	2	1	4	4	X	X	2	4	X	4	4	2	X
Butyl Stearate	2	4	1	4	4	X	X	4	4	4	4	4	2	X
Butylene	2	4	1	3	4	4	4	4	4	4	4	4	2	4
Butyraldehyde	4	2	4	4	4	4	4	2	4	4	4	4	4	4
Butyric Acid	4	2	2	4	4	4	X	2	4	X	X	4	X	X
Calcine Liquors	1	1	1	X	X	4	4	1	X	X	X	X	1	X
Calcium Acetate	2	1	4	2	4	4	4	1	4	1	1	2	4	4
Calcium Bisulfite	2	1	2	2	2	3	3	1	4	4	4	1	3	3
Calcium Carbonate	1	1	1	1	1	3	3	1	1	1	1	1	1	1
Calcium Chloride	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Calcium Cyanide	1	1	X	1	1	X	X	1	1	1	1	1	X	1
Calcium Hydroxide	1	1	1	1	1	4	2	1	1	1	1	1	1	1
Calcium Hypochlorite	2	1	1	2	2	4	4	1	2	2	2	1	2	2
Calcium Nitrate	1	1	1	1	1	1	1	1	1	1	1	1	1	2
Calcium Phosphate	1	1	1	2	1	1	1	1	1	1	1	1	X	1
Calcium Salts	1	1	1	1	1	1	1	1	1	1	1	1	1	2
Calcium Silicate	1	1	1	1	1	X	X	1	1	1	1	1	X	X
Calcium Sulfide	1	1	1	1	2	4	1	1	2	2	2	1	1	1
Calcium Sulfite	1	1	1	1	2	4	1	1	2	2	2	1	1	1
Calcium Thiosulfate	2	1	1	1	2	4	1	1	2	2	2	1	1	1
Caliche Liquors	1	1	1	1	1	1	1	1	1	1	1	1	1	2
Cane Sugar Liquors	1	1	1	1	1	4	4	1	1	1	1	1	1	1
Caproic Aldehyde	X	2	4	X	X	4	4	2	2	2	2	X	4	2
Carbamate	3	2	1	2	4	4	4	2	4	4	4	2	1	X
Carbitol	2	2	2	2	2	4	4	2	2	2	2	2	2	2
Carbolic Acid Phenol	4	2	1	4	4	4	3	2	4	4	4	4	1	4
Carbon Bisulfide	4	4	1	4	4	3	X	4	4	4	4	4	1	4
Carbon Dioxide	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Carbon Dioxide (Explosive Decompression Use)	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Carbon Disulfide	4	4	1	4	4	3	X	4	4	4	4	4	1	4

**NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com**

**SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME**

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
 1 = Satisfactory
 2 = Fair (Usually OK for Static Seal)
 3 = Doubtful (Sometimes OK for Static Seal)
 4 = Unsatisfactory
 X = Insufficient Data

FLUID NAME	MATERIAL	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Carbon Monoxide	1	1	1	2	2	X	1	1	2	2	2	2	2	2	1
Carbon Tetrachloride	2	4	1	4	4	4	4	4	4	4	4	4	4	2	4
Carbonic Acid	2	1	1	1	2	1	1	1	2	1	1	1	1	1	1
Castor Oil	1	2	1	1	1	1	1	2	1	1	1	1	1	1	1
Cellosolve	4	2	4	4	4	4	4	2	4	4	4	4	4	4	4
Cellosolve Butyl	4	2	4	4	4	4	4	2	4	4	4	4	4	4	4
Cellosolve, Acetate	4	2	4	4	4	4	4	2	4	4	4	4	4	4	4
Cellugard	1	1	1	1	1	3	4	1	1	1	1	1	1	1	1
Cellultherm 2505A	2	4	1	4	4	2	4	4	4	4	4	4	4	2	4
Cetane (Hexadecane)	1	4	1	2	4	1	4	4	4	4	4	4	2	3	4
China Wood Oil (Tung Oil)	1	4	1	2	4	X	3	3	4	4	4	3	2	2	4
Chlordane	2	4	1	3	4	X	X	4	4	4	4	3	2	4	4
Chlorextol	2	4	1	2	4	2	4	4	4	4	4	4	4	2	4
Chlorinated Solvents, Dry	4	4	1	4	4	4	4	4	4	4	4	4	1	4	4
Chlorinated Solvents, Wet	4	4	1	4	4	4	4	4	4	4	4	4	1	4	4
Chlorine Dioxide	4	3	1	4	4	4	4	3	4	4	4	3	2	X	4
Chlorine Dioxide, 8% Cl as NaClO2 in solution	4	4	1	4	4	4	4	4	4	4	4	4	2	X	4
Chlorine Trifluoride	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Chlorine, Dry	4	X	2	2	4	4	X	X	4	4	4	2	X	4	4
Chlorine, Wet	4	X	2	4	4	4	X	X	4	4	4	2	X	X	4
Chloroacetic Acid	4	2	4	4	4	4	4	2	4	4	4	1	4	X	4
Chloroacetone	4	1	4	4	4	4	4	2	4	4	4	4	4	4	4
Chlorobenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4	4
Chlorobenzene (Mono)	4	4	1	4	4	4	4	4	4	4	4	4	2	4	4
Chlorobromo Methane	4	2	1	4	4	4	4	2	4	4	4	4	2	4	4
Chlorobutadiene	4	4	1	4	4	4	4	4	4	4	4	4	2	4	4
Chlorododecane	4	4	1	4	4	4	4	4	4	4	4	4	1	4	4
Chloroform	4	4	1	4	4	4	4	4	4	4	4	4	4	4	4
Chlorosulphonic Acid	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Chlorotoluene	4	4	1	4	4	4	4	4	4	4	4	4	2	4	4
Chlorox	2	2	1	2	4	4	4	2	4	4	4	2	1	X	4
Chrome Alum	1	1	1	1	1	4	X	1	1	1	1	1	X	1	4
Chrome Plating Solutions	4	2	1	4	4	4	4	2	4	4	4	4	2	2	4
Circo Light Process Oil	1	4	1	2	4	1	1	4	4	4	4	2	1	4	4
Citric Acid	1	1	1	1	1	X	1	1	1	1	1	1	1	1	1
City Service #65 #120 #250	1	4	1	2	4	1	2	4	4	4	4	4	1	4	4
City Service Koolmoter-AP Gear Oil 140-EP lube	1	4	1	2	4	1	1	4	4	4	4	2	1	4	4
City Service Pacemaker #2	1	4	1	2	4	1	2	4	4	4	4	4	1	4	4
Cobalt Chloride	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2
Cobalt Chloride, 2N	1	1	1	1	1	4	4	1	1	1	1	1	1	1	1
Cocoonut Oil	1	3	1	3	4	1	3	3	4	4	4	3	1	1	1
Cod Liver Oil	1	1	1	2	4	1	1	1	4	4	4	2	1	2	4
Coffee	1	1	1	1	1	4	4	1	1	1	1	1	1	1	1
Coke Oven Gas	4	4	1	4	4	4	4	4	4	4	4	4	2	2	4
Coliche Liquors	2	2	X	1	2	X	X	2	1	1	1	X	X	X	4
Convelex 10	4	X	X	4	4	X	2	4	4	4	4	4	X	4	4
Coolanol 20 25R 35R 40& 45A (Monsanto)	1	3	1	2	4	4	1	4	4	4	4	2	1	4	4
Copper Acetate	2	1	4	2	4	4	4	1	4	1	1	2	4	4	4
Copper Chloride	1	1	1	2	1	1	1	1	1	1	1	2	1	1	1
Copper Cyanide	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Copper Salts	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Copper Sulfate	1	1	1	1	2	4	1	2	2	2	2	1	1	1	1
Copper Sulfate 10%	1	1	1	1	2	4	2	2	2	2	2	1	1	1	1
Copper Sulfate 50%	1	1	1	1	2	4	3	2	2	2	2	1	1	1	1
Corn Oil	1	3	1	3	4	1	1	3	4	4	4	2	1	1	1
Cottonseed Oil	1	3	1	3	4	1	1	3	4	4	4	2	2	1	1
Creosote, Coal Tar	1	4	1	2	4	1	3	4	4	4	4	4	1	4	4
Creosote, Wood	1	4	1	2	4	1	3	4	4	4	4	4	1	4	4
Cresols	4	4	2	4	4	4	X	4	4	4	4	4	X	4	4
Cresylic Acid	4	4	1	4	4	4	4	4	4	4	4	4	X	4	4
Crude Oil	2	4	1	4	4	1	X	4	4	4	4	4	2	4	4
Cumene	4	4	1	4	4	4	4	4	4	4	4	4	2	4	4

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME



111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:

1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME

MATERIAL	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Cutting Oil	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Cyclohexane	1	4	1	3	4	2	1	4	4	4	4	4	1	4
Cyclohexanol	1	4	1	2	4	X	X	4	4	4	4	2	1	4
Cyclohexanone	4	2	4	4	4	4	4	2	4	4	4	4	4	4
DTE 20 Series, Mobil	2	4	1	1	X	2	1	4	X	X	2	2	2	4
DTE named series, Mobil, light-heavy	1	4	1	2	4	X	1	4	4	X	3	1	1	3
Decalin	4	4	1	4	4	X	X	4	4	4	4	4	1	4
Decane	1	4	1	3	4	1	2	4	4	4	4	3	1	2
Delco Brake Fluid	3	1	4	2	1	X	X	2	X	X	X	2	4	3
Denatured Alcohol	1	1	1	1	1	4	4	1	1	1	1	1	1	1
Detergent, Water Solution	1	1	1	2	2	4	4	1	2	2	2	2	1	1
Developing Fluids (Photo)	1	2	1	1	2	X	X	2	2	1	1	1	1	1
Dexron	1	4	1	2	4	1	2	4	4	4	4	4	2	4
Di-ester Lubricant MIL-L-7808	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Di-ester Synthetic Lubricants	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Diacetone	4	1	4	4	4	4	4	1	4	4	4	4	4	4
Diacetone Alcohol	4	1	4	2	4	4	4	1	4	4	4	2	4	4
Diazinon	3	4	2	3	4	X	X	4	4	4	4	3	2	4
Dibenzyl Ether	4	2	4	4	4	X	2	2	4	4	4	4	X	X
Dibenzyl Sebacate	4	2	2	4	4	4	2	2	4	4	4	4	3	3
Dibromoethyl Benzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Dibutyl Ether	4	3	3	4	4	3	2	3	4	4	4	4	3	4
Dibutyl Phthalate	4	2	3	4	4	4	3	3	4	4	4	4	3	2
Dibutyl Sebacate	4	2	2	4	4	4	4	2	4	4	4	4	2	2
Dibutylamine	4	4	4	3	4	4	4	4	4	4	4	4	4	3
Dichloro-Butane	2	4	1	4	4	4	4	4	4	4	4	4	2	4
Dichloro-Isopropyl Ether	4	3	3	4	4	3	2	4	4	4	4	4	3	4
Dicyclohexylamine	3	4	4	4	4	4	4	4	4	4	4	4	4	X
Diesel Oil	1	4	1	3	4	1	3	4	4	4	4	3	1	4
Diethyl Ether	4	4	4	3	4	3	1	4	4	4	4	4	3	4
Diethyl Sebacate	2	2	2	4	4	4	2	4	4	4	4	4	2	2
Diethylamine	2	2	4	2	2	4	3	2	2	2	2	3	4	2
Diethylene Glycol	1	1	1	1	1	2	4	1	1	1	1	1	1	2
Diffluorodibromomethane	4	2	X	4	4	4	4	2	4	4	4	4	X	4
Diisobutyl Ketone	X	1	X	X	X	X	X	1	X	X	X	X	X	X
Diisobutylene	2	4	1	4	4	4	4	4	4	4	4	4	3	4
Diisooctyl Sebacate	3	3	2	4	4	4	4	4	4	4	4	4	3	3
Diisopropyl Ketone	4	1	4	4	4	4	4	1	4	4	4	4	4	4
Dimethyl Formamide (DMF)	2	1	4	3	4	4	4	2	X	X	4	4	4	2
Dimethyl Phthalate	4	2	2	4	4	4	X	2	4	4	4	4	2	X
Dinitro Toluene	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Dioctyl Phthalate	4	2	2	4	4	4	2	4	4	4	4	4	2	3
Dioctyl Sebacate	4	2	2	4	4	4	2	2	4	4	4	4	3	3
Dioxane	4	2	4	4	4	4	4	2	4	4	4	4	4	4
Dioxolane	4	2	4	4	4	4	4	3	4	4	4	4	4	4
Dipentene	2	4	1	4	4	4	4	4	4	4	4	4	3	4
Diphenyl	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Diphenyl Oxides	4	4	1	4	4	4	4	4	4	4	4	4	2	3
Dow Chemical 50-4	X	1	4	2	1	X	X	2	X	X	X	2	4	X
Dow Chemical ET378	4	X	X	4	4	3	2	4	4	4	4	4	X	4
Dow Chemical ET588	3	1	4	2	1	X	X	2	X	X	X	2	4	X
Dow Corning -11	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -1265 Fluorosilicone Fluid	2	1	1	1	1	1	1	1	1	1	1	1	3	1
Dow Corning -200	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -3	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -33	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -4	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -44	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -5	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -510	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -55	2	1	1	1	1	1	1	1	1	1	1	1	1	2
Dow Corning -550	2	1	1	1	1	1	1	1	1	1	1	1	2	3

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone	
Dow Corning -704	2	1	1	1	1	1	1	1	1	1	1	1	2	3	
Dow Corning -705	2	1	1	1	1	1	1	1	1	1	1	1	1	2	3
Dow Corning -710	2	1	1	1	1	1	1	1	1	1	1	1	1	2	3
Dow Guard	1	1	1	1	1	3	3	1	1	1	1	1	1	1	1
Dowtherm, 209	3	1	4	2	X	X	X	2	X	X	X	X	3	3	
Dowtherm, A	4	4	1	4	4	4	4	4	4	4	4	4	4	2	4
Dowtherm, E	4	4	1	4	4	4	4	4	4	4	4	4	4	2	4
Drinking Water	1	1	1	2	1	4	4	1	1	1	1	1	1	1	1
Dry Cleaning Fluids	3	4	1	4	4	4	4	4	4	4	4	4	4	2	4
Elco 28-EP lubricant	1	4	1	3	4	1	1	4	4	4	4	4	4	1	2
Epichlorohydrin	4	2	4	4	4	4	4	2	4	4	4	4	4	4	4
Epoxy Resins	X	1	4	1	X	X	X	1	X	X	X	X	X	X	X
Esam-6 Fluid	X	1	4	2	1	X	X	2	X	X	X	X	2	4	X
Esso Fuel 208	1	4	1	2	4	1	4	4	4	4	4	3	1	4	4
Esso Golden Gasoline	2	4	1	4	4	4	4	4	4	4	4	4	4	1	4
Esso Motor Oil	1	4	1	3	4	1	4	4	4	4	4	4	4	1	4
Esso Transmission fluid (Type A)	1	4	1	2	4	1	3	4	4	4	4	4	1	4	4
Esso WS2812 (MIL-L-7808A)	1	4	1	4	4	2	4	4	4	4	4	4	4	1	4
Esso XP90-EP lubricant	1	4	1	2	4	1	1	4	4	4	4	2	1	4	4
Esstic 42, 43	1	4	1	2	4	1	2	4	4	4	4	4	4	1	4
Ethane	1	4	1	2	4	1	3	4	4	4	4	2	3	4	4
Ethanol	3	1	3	1	1	4	4	1	1	1	1	1	1	1	2
Ethanol Amine	2	2	4	2	2	4	3	2	2	2	2	3	4	2	2
Ethers	4	3	3	4	4	3	2	4	4	4	4	4	3	4	4
Ethyl Acetate-Organic ester	4	2	4	4	4	4	4	2	4	4	4	4	4	2	2
Ethyl Acetoacetate	4	2	4	4	3	4	4	2	3	3	3	4	4	2	2
Ethyl Acrylate	4	2	4	4	4	4	4	2	4	4	4	4	4	2	2
Ethyl Alcohol	3	1	3	1	1	4	4	1	1	1	1	1	1	1	2
Ethyl Benzene	4	4	1	4	4	4	4	4	4	4	4	4	1	4	4
Ethyl Benzoate	4	4	1	4	4	4	4	4	4	4	4	4	4	1	4
Ethyl Bromide	2	4	1	4	X	X	X	4	4	4	4	4	1	X	4
Ethyl Cellosolve	4	2	4	4	4	4	4	2	4	4	4	4	4	4	4
Ethyl Cellulose	2	2	4	2	2	4	2	2	2	2	2	2	4	2	2
Ethyl Chloride	1	3	1	4	4	3	2	4	2	1	4	4	1	4	4
Ethyl Chlorocarbonate	4	2	1	4	4	4	4	4	4	4	4	4	2	4	4
Ethyl Chloroformate	4	2	4	4	4	4	4	3	4	4	4	4	4	4	4
Ethyl Ether	3	3	4	4	4	4	2	3	4	4	4	4	3	4	4
Ethyl Formate	4	2	1	2	4	X	X	2	4	4	4	2	1	X	4
Ethyl Hexanol	1	1	1	1	1	4	4	1	1	1	1	1	1	1	2
Ethyl Mercaptan	4	X	2	3	4	X	X	4	4	4	4	3	X	3	4
Ethyl Oxalate	4	1	2	4	4	4	X	4	4	1	4	4	2	4	4
Ethyl Pentachlorobenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4	4
Ethyl Silicate	1	1	1	1	2	X	X	1	2	2	2	2	1	X	4
Ethylacrylic Acid	4	2	X	2	4	4	4	2	4	4	4	4	4	4	4
Ethylcyclopentane	1	4	1	3	4	2	1	4	4	4	4	4	1	4	4
Ethylene Chloride	4	4	2	4	4	4	4	4	4	4	4	4	2	4	4
Ethylene Chlorohydrin	4	2	1	2	2	4	4	2	2	2	2	2	2	3	3
Ethylene Diamine	1	1	4	1	2	4	4	1	2	1	1	2	4	1	1
Ethylene Dibromide	4	3	1	4	4	4	4	3	4	4	4	4	3	4	4
Ethylene Dichloride	4	3	1	4	4	4	4	3	4	4	4	4	3	4	4
Ethylene Glycol	1	1	1	1	1	4	2	1	1	1	1	1	1	1	1
Ethylene Oxide	4	3	4	4	4	4	4	3	4	4	4	4	4	4	4
Ethylene Oxide, (12%) and Freon 12 (80%)	3	2	4	4	4	4	4	2	4	4	4	4	4	4	4
Ethylene Trichloride	4	3	1	4	4	4	4	3	4	4	4	4	3	4	4
Ethylmorpholine Stannous Octotate (50/50 mixture)	4	2	4	X	4	X	X	2	X	X	X	X	X	X	X
F-60 Fluid (Dow Corning)	1	1	1	1	1	1	1	1	1	1	1	1	1	1	4
F-61 Fluid (Dow Corning)	1	1	1	1	1	1	1	1	1	1	1	1	1	1	4
FC-43 Heptacosulfurotri-butylamine	1	1	1	1	4	X	X	1	X	X	X	1	1	1	1
FC75 & FC77 (Fluorocarbon)	1	1	2	1	4	X	X	1	X	X	X	1	2	1	1
Fatty Acids	2	3	1	2	4	X	X	3	4	4	4	2	X	3	4
Ferric Chloride	1	1	1	2	1	1	1	1	1	1	1	1	2	1	2
Ferric Nitrate	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME



111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:

- 1 = Satisfactory
- 2 = Fair (Usually OK for Static Seal)
- 3 = Doubtful (Sometimes OK for Static Seal)
- 4 = Unsatisfactory
- X = Insufficient Data

FLUID NAME	MATERIAL	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Fisher Reagent	X	2	X	X	X	X	X	X	X	X	X	X	X	X	X
Fluorolube	1	1	2	1	4	X	X	1	X	X	X	1	2	1	
Formaldehyde	3	2	4	3	3	4	4	2	2	2	2	2	4	2	
Freon, 11	4	4	2	4	4	4	X	4	X	X	4	1	2	4	
Freon, 112	2	4	1	2	4	X	X	4	X	X	4	2	X	4	
Freon, 113	1	4	2	1	2	X	1	4	X	X	4	1	X	4	
Freon, 114	1	1	1	1	1	X	X	1	X	X	1	X	X	4	
Freon, 114B2	2	4	2	2	4	X	X	4	X	X	4	1	X	4	
Freon, 115, 116	1	1	2	1	1	X	X	1	X	X	1	X	X	X	
Freon, 12	2	3	3	1	1	X	1	3	4	4	2	1	3	4	
Freon, 12 and ASTM Oil #2 (50/50 Mixture)	2	4	1	3	4	X	X	4	4	4	4	2	2	4	
Freon, 12 and Suniso 4G (50/50 Mixture)	2	4	1	3	4	X	X	4	4	4	4	2	2	4	
Freon, 13	1	1	1	1	1	X	X	1	X	1	1	1	1	4	4
Freon, 13B1	1	1	1	1	1	X	X	1	X	X	1	1	2	4	
Freon, 14	1	1	1	1	1	X	1	1	X	X	1	1	X	4	
Freon, 21	4	4	4	3	4	X	X	4	4	4	4	4	X	4	
Freon, 22	4	3	4	1	1	2	4	3	X	X	1	1	4	4	
Freon, 22 and ASTM Oil #2 (50/50 Mixture)	4	4	2	2	4	2	X	4	X	X	4	X	2	4	
Freon, 31	4	1	4	1	2	X	X	1	X	X	2	2	X	X	
Freon, 32	1	1	4	1	1	X	X	1	X	X	1	1	X	X	
Freon, 502	2	1	2	1	1	X	X	1	X	X	1	X	X	X	
Freon, BF	2	4	1	2	4	X	X	4	X	X	4	2	X	4	
Freon, C318	1	1	2	1	1	X	X	1	X	X	1	1	X	X	
Freon, K-142b	1	1	4	1	1	X	X	1	X	X	2	1	X	X	
Freon, K-152a	1	1	4	1	1	X	X	1	X	X	1	4	X	X	
Freon, MF	2	4	2	4	4	X	3	4	X	X	4	1	X	4	
Freon, PCA	1	4	2	1	2	X	1	4	X	X	4	1	X	4	
Freon, TF	1	4	2	1	2	X	1	4	X	X	4	1	X	4	
Fuel Oil, #6	2	4	1	4	4	1	2	4	4	4	4	4	1	1	
Fuel Oil, 1, and 2	1	4	1	2	4	1	2	4	4	4	4	3	1	4	
Fuel Oil, Acidic	1	4	1	2	4	1	2	4	4	4	4	4	1	1	
Fumaric Acid	1	2	1	2	2	4	X	4	2	1	3	2	1	2	
Fuming Sulphuric Acid (20/25% Oleum)	4	4	1	4	4	4	4	4	4	4	4	4	X	4	
Furan (Furfuran)	4	3	X	4	4	4	X	4	4	4	4	4	X	X	
Furfural	4	2	4	4	4	4	3	2	4	4	4	3	X	4	
Furfuraldehyde	4	2	4	4	4	4	X	2	4	4	4	4	X	4	
Furfuryl Alcohol	4	2	X	4	4	4	4	2	4	4	4	4	4	4	
Furyl Carbinol	4	2	X	4	4	4	4	2	4	4	4	4	4	4	
Fyrquel 150 220 300 550	4	1	1	4	4	4	4	1	4	4	4	4	2	1	
Gallic Acid	2	2	1	2	2	4	4	2	X	1	1	2	1	X	
Gasoline	1	4	1	4	4	4	2	4	4	4	4	4	1	4	
Gelatin	1	1	1	1	1	4	4	1	1	1	1	1	1	1	
Girling Brake Fluid	3	1	4	2	1	X	X	2	X	X	X	2	4	X	
Glacial Acetic Acid	2	2	4	4	2	4	4	2	2	2	2	2	4	4	
Glauber's Salt	4	2	1	2	4	4	X	2	4	2	2	2	1	X	
Glucose	1	1	1	1	1	X	4	1	1	1	1	1	1	1	
Glycerine - Glycerol	1	1	1	1	1	4	4	1	1	1	1	1	1	1	
Glycols	1	1	1	1	1	4	4	1	1	1	1	1	1	1	
Grease Petroleum Base	1	4	1	3	4	1	1	4	4	4	4	4	1	4	
Green Sulphate Liquor	2	1	1	2	2	4	4	1	2	2	2	2	2	X	
Gulf Endurance Oils	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Gulf FR Fluids (Emulsion)	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Gulf FR G-Fluids	1	1	1	1	1	4	2	1	1	1	1	1	1	1	
Gulf FR P-Fluids	4	2	2	4	4	4	4	2	4	4	4	4	2	1	
Gulf Harmony Oils	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Gulf High Temperature Grease	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Gulf Legion Oils	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Gulf Paramount Oils	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Gulf Security Oils	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Gulfcrown Grease	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
HEF-2 (High Energy Fuel)	2	4	1	4	4	4	4	4	4	4	4	4	2	4	
Halothane	4	4	1	4	4	4	4	4	4	4	4	4	2	4	

**NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com**

**SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME**

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
 1 = Satisfactory
 2 = Fair (Usually OK for Static Seal)
 3 = Doubtful (Sometimes OK for Static Seal)
 4 = Unsatisfactory
 X = Insufficient Data

FLUID NAME	MATERIAL	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Halowax Oil	4	4	1	4	4	X	X	4	4	4	4	4	1	4	
Hannifin Lube A	1	4	1	1	2	1	1	4	4	4	4	1	1	2	
Heavy Water	1	1	X	2	1	4	4	1	1	1	1	1	1	1	
Hellum	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Hexyl Alcohol	1	3	1	2	1	4	4	3	1	1	1	2	2	2	
HiLo MS #1	4	1	4	4	4	4	4	2	4	4	4	4	3	3	
High Viscosity Lubricant, H2	1	1	1	2	1	4	4	1	2	X	X	X	2	1	
High Viscosity Lubricant, U4	1	1	1	2	1	4	4	1	2	X	X	X	2	1	
Houghto-Safe 1010 phosphate ester	4	1	1	4	4	4	X	1	4	4	4	4	2	3	
Houghto-Safe 1055 phosphate ester	4	1	1	4	4	4	X	1	4	4	4	4	2	3	
Houghto-Safe 1120 phosphate ester	4	2	1	4	4	4	4	1	4	4	4	4	2	3	
Houghto-Safe 271 (Water & Glycol Base)	1	1	2	2	1	4	4	2	X	X	X	X	2	2	
Houghto-Safe 416 & 500 Series	1	1	X	X	X	X	X	X	X	X	X	X	X	X	
Houghto-Safe 5040 (Water/Oil emulsion)	1	4	1	2	4	4	4	4	4	4	4	4	2	3	
Houghto-Safe 620 Water/Glycol	1	1	2	2	1	4	4	2	X	X	X	X	2	2	
Hydraulic Oil, Petroleum Base, Industrial	1	4	1	2	4	1	1	4	4	4	4	2	1	2	
Hydrazine	2	1	4	2	2	X	4	1	X	X	1	2	4	2	
Hydro-Drive MIH-10 (Petroleum Base)	1	4	1	2	4	1	2	4	4	4	4	4	1	2	
Hydro-Drive MIH-50 (Petroleum Base)	1	4	1	2	4	1	2	4	4	4	4	4	1	2	
Hydrobromic Acid	4	1	1	4	4	4	4	1	4	1	1	1	3	4	
Hydrobromic Acid 40%	4	1	1	2	4	4	4	1	4	1	1	1	3	4	
Hydrocarbons, Saturated	1	4	1	2	4	1	2	4	4	4	4	3	1	4	
Hydrochloric Acid, 3 Molar to 158°F	2	1	1	2	3	3	4	1	X	X	3	1	3	4	
Hydrochloric Acid, Concentrated Room Temp.	2	2	1	X	X	X	X	X	X	X	X	X	X	X	
Hydrochloric Acid, Concentrated to 158°F	4	4	4	4	4	4	4	4	X	X	4	X	4	4	
Hydrocyanic Acid	2	1	1	2	2	4	X	1	2	1	1	1	2	3	
Hydrofluosilicic Acid	2	1	1	2	2	X	X	1	X	1	1	1	4	4	
Hydrogen Gas, Cold	1	1	1	1	2	2	1	1	1	1	2	1	3	3	
Hydrogen Gas, Hot	1	1	1	1	2	2	1	1	1	1	2	1	3	3	
Hydrogen Peroxide	2	1	1	1	2	4	X	1	2	2	2	2	1	1	
Hydrogen Peroxide 90%	4	3	1	4	4	4	X	3	4	4	4	3	2	2	
Hydrogen Sulfide Dry Cold	1	1	4	1	1	4	X	1	1	1	1	1	3	3	
Hydrogen Sulfide Dry Hot	4	1	4	2	4	4	X	1	4	4	4	3	3	3	
Hydrogen Sulfide Wet Cold	4	1	4	1	4	4	X	1	4	4	4	2	3	3	
Hydrogen Sulfide Wet Hot	4	1	4	2	4	4	X	1	4	4	4	3	3	3	
Hydrolube-Water/Ethylene Glycol	1	1	1	2	1	4	4	2	X	X	X	X	2	2	
Hydroquinone	3	2	2	4	4	4	X	4	4	2	2	4	2	X	
Hydye	2	1	4	2	2	4	X	2	2	2	2	X	4	4	
Hyjet IV and IVA	4	1	4	4	4	4	4	2	4	4	4	4	4	4	
Hypochlorous Acid	4	2	1	4	4	4	X	2	4	2	2	1	X	X	
Industron FF44	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Industron FF48	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Industron FF53	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Industron FF80	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Iodine	2	2	1	4	2	X	X	2	X	4	X	2	1	X	
Iodine Pentafluoride	4	4	4	4	4	4	4	4	4	4	4	4	4	4	
Iso Octane	1	4	1	2	4	1	2	4	4	4	4	1	1	4	
Iso-Butyl N-Butyrate	4	1	1	4	4	4	X	1	4	4	4	4	1	X	
Isobutyl Alcohol	2	1	1	1	2	4	4	1	2	1	1	1	2	1	
Isododecane	1	4	1	2	4	4	X	4	4	4	4	2	1	4	
Isophorone (Ketone)	4	2	4	4	4	4	4	2	4	4	4	4	4	4	
Isopropanol	2	1	1	2	2	4	4	1	2	1	1	1	2	1	
Isopropyl Acetate	4	2	4	4	4	4	4	2	4	4	4	4	2	4	
Isopropyl Alcohol	2	1	1	2	2	4	4	1	2	1	1	1	2	1	
Isopropyl Chloride	4	4	1	4	4	4	4	4	4	4	4	4	2	4	
Isopropyl Ether	2	4	4	3	4	3	2	4	4	4	4	3	3	4	
JP-10	3	4	1	4	4	4	3	4	X	X	4	X	1	4	
JP-4 (MIL-T-5624)	1	4	1	4	4	2	2	4	4	4	4	4	2	4	
JP-5 (MIL-T-5624)	1	4	1	4	4	2	2	4	4	4	4	4	2	4	
JP-6 (MIL-J-25656)	1	4	1	4	4	2	2	4	4	4	4	4	2	4	
JP-8 (MIL-T-83133)	1	4	1	3	4	1	1	4	X	X	4	X	2	4	
JP-9 (MIL-F-81912)	3	4	1	4	4	4	3	4	X	X	4	X	2	4	

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME



PNEU-DRAULICS

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
 1 = Satisfactory
 2 = Fair (Usually OK for Static Seal)
 3 = Doubtful (Sometimes OK for Static Seal)
 4 = Unsatisfactory
 X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
JP-9 -11	4	4	1	4	4	4	4	4	X	X	4	X	2	4
Kel F Liquids	1	1	2	X	1	X	X	1	X	X	X	1	2	1
Kerosene (Similar to RP-1 and JP-1)	1	4	1	2	4	1	1	4	4	4	4	4	1	4
Keystone #87HX-Grease	1	4	1	4	4	1	1	4	4	4	4	4	1	4
Lacquer Solvents	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Lacquers	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Lactams-Amino Acids	4	2	4	2	4	X	X	2	4	4	4	2	4	X
Lactic Acid Cold	1	1	1	1	1	4	X	1	1	1	1	1	1	1
Lactic Acid Hot	4	4	1	4	4	4	X	4	4	4	4	3	2	2
Lactones (Cyclic Esters)	4	2	4	4	4	4	4	2	4	4	4	4	4	2
Lard Animal Fat	1	2	1	2	4	1	1	2	4	4	4	4	1	2
Lead Acetate	2	1	4	2	4	4	4	1	4	1	1	1	4	4
Lead Nitrate	1	1	X	1	1	X	X	1	1	1	1	1	1	2
Lead Sulphamate	2	1	1	1	2	4	X	1	2	2	2	1	1	2
Lehigh X1169	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Lehigh X1170	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Ligroin (Petroleum Ether or Benzene)	1	4	1	2	4	1	2	4	4	4	4	3	1	4
Lindol, Hydraulic Fluid (Phosphate ester type)	4	1	2	4	4	4	4	1	4	4	4	4	3	3
Linoleic Acid	2	4	2	2	4	X	X	4	4	4	4	2	X	2
Linseed Oil	1	3	1	3	4	1	2	3	4	4	4	2	1	1
Liquid Oxygen (LOX)	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Liquid Petroleum Gas (LPG)	1	4	1	2	4	3	1	4	4	4	4	4	3	3
Liquimoly	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Lubricating Oils, Di-ester	2	4	1	3	4	2	X	4	4	4	4	X	2	4
Lubricating Oils, SAE 10, 20, 30, 40, 50	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Lubricating Oils, petroleum base	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Lye Solutions	2	1	2	2	2	4	1	2	2	2	1	1	2	2
MCS 312	4	4	1	4	4	4	X	4	4	4	4	X	1	1
MCS 352	4	1	4	4	4	4	4	2	4	4	4	4	3	3
MCS 463	4	1	4	4	4	4	4	2	4	4	4	4	3	3
MIL-A-6091	2	1	1	1	1	4	4	1	1	1	1	1	1	1
MIL-C-4339	1	4	1	4	4	1	1	4	4	4	4	4	1	3
MIL-C-7024	1	4	1	2	4	2	1	4	4	4	4	4	1	4
MIL-C-8188	2	4	2	4	4	3	4	4	4	4	4	4	2	4
MIL-E-9500	1	1	1	1	1	4	4	1	1	1	1	1	1	1
MIL-F-16884	1	4	1	3	4	1	3	4	4	4	4	3	1	4
MIL-F-17111	1	4	1	2	4	1	3	4	4	4	4	2	2	4
MIL-F-25558 (RJ-1)	1	4	1	2	4	1	1	4	4	4	4	2	1	4
MIL-F-25656	1	4	1	4	4	2	2	4	4	4	4	4	2	4
MIL-F-5566	2	1	1	2	2	4	2	1	2	1	1	1	1	1
MIL-F-81912 (JP-9)	3	4	1	4	4	4	3	4	X	X	4	X	2	4
MIL-F-82522 (RJ-4)	2	4	1	4	4	1	1	4	1	1	1	X	1	4
MIL-G-10924	1	4	1	2	4	2	1	4	4	4	4	2	1	4
MIL-G-15793	1	4	1	2	4	1	1	4	4	4	4	2	2	4
MIL-G-21568	1	1	1	1	1	1	1	1	1	1	1	1	1	4
MIL-G-25013	1	1	1	2	1	1	3	1	4	4	2	2	1	4
MIL-G-25537	1	4	1	2	4	2	1	4	4	4	4	2	1	4
MIL-G-25760	2	4	1	2	4	2	2	4	4	4	4	2	2	4
MIL-G-3278	2	4	1	4	4	1	2	4	4	4	4	4	2	4
MIL-G-3545	1	4	1	2	4	1	1	4	4	4	4	2	1	4
MIL-G-4343	2	3	1	2	1	1	3	1	1	1	1	1	1	3
MIL-G-5572	1	4	1	4	4	2	2	4	4	4	4	4	1	4
MIL-G-7118	2	4	1	2	4	3	3	4	4	4	4	2	1	4
MIL-G-7187	1	4	1	4	4	1	1	4	4	4	4	4	1	4
MIL-G-7421	2	4	1	2	4	4	2	4	4	4	4	2	2	4
MIL-G-7711	1	4	1	4	4	2	1	4	4	4	4	4	1	2
MIL-H-13910	1	1	1	1	1	2	4	1	1	1	1	1	2	4
MIL-H-19457	4	2	1	4	4	4	4	1	4	4	4	4	4	3
MIL-H-22251	2	1	X	2	2	X	X	1	X	X	X	2	X	4
MIL-H-27601	1	4	1	2	4	1	3	4	4	4	4	3	2	4
MIL-H-46170 -15°F to +400°F	1	4	1	2	4	2	2	4	4	4	4	2	1	4
MIL-H-46170 -20°F to +275°F	1	4	1	2	4	2	2	4	4	4	4	2	1	4

**NATIONWIDE
 CALL 1-800-333-SEAL
 FAX (859) 887-4165
 www.pneu-draulics.com**

**SALES OFFICE HOURS
 7:30 A.M. to 5:30 P.M.
 EASTERN STANDARD TIME**

111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



APPENDIX

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
MIL-H-46170 -55°F to +275°F	1	4	1	2	4	2	2	4	4	4	4	2	1	4
MIL-H-46170 -65°F to +275°F	1	4	1	2	4	2	2	4	4	4	4	2	1	4
MIL-H-5606 -65°F to +235°F	1	4	1	2	4	2	2	4	4	4	4	2	1	4
MIL-H-5606 -65°F to +275°F	1	4	1	2	4	2	2	4	4	4	4	2	1	4
MIL-H-6083	1	4	1	1	4	1	1	4	4	4	2	2	1	4
MIL-H-7083	1	1	2	2	2	4	4	1	3	3	2	2	1	1
MIL-H-8446 (MLO-8515)	2	4	1	1	4	3	4	4	4	4	4	X	1	4
MIL-J-5161	2	4	1	4	4	1	2	4	4	4	4	4	1	4
MIL-L-15016	1	4	1	2	4	1	1	4	4	4	4	2	2	4
MIL-L-15017	1	4	1	2	4	1	1	4	4	4	4	2	2	4
MIL-L-17331	1	4	1	X	4	X	X	4	4	4	4	X	X	4
MIL-L-2104	1	4	1	2	4	1	1	4	4	4	4	3	1	4
MIL-L-21260	1	4	1	2	4	1	1	4	4	4	4	2	1	4
MIL-L-23699	2	4	1	3	4	3	3	4	4	4	4	3	2	4
MIL-L-25681	2	1	1	2	2	2	3	1	2	2	2	2	2	4
MIL-L-3150	1	4	1	2	4	2	2	4	4	4	4	2	1	4
MIL-L-6081	1	4	1	2	4	1	1	4	4	4	4	2	1	4
MIL-L-6082	1	4	1	2	4	1	1	4	4	4	4	2	1	3
MIL-L-6085	2	4	1	4	4	2	3	4	4	4	4	4	2	4
MIL-L-6387	2	4	1	4	4	2	1	4	4	4	4	4	2	4
MIL-L-7808	2	4	1	4	4	2	4	4	4	4	4	4	2	4
MIL-L-7870	1	4	1	2	4	1	2	4	4	4	4	4	1	4
MIL-L-9000	1	4	1	2	4	1	3	4	4	4	4	2	2	4
MIL-L-9236	2	4	1	4	4	2	2	4	4	4	4	4	2	4
MIL-O-3503	1	4	1	2	4	2	1	4	4	4	4	2	1	4
MIL-P-27402	2	1	X	2	2	X	X	1	X	X	X	2	X	4
MIL-R-25576 (RP-1)	1	4	1	2	4	1	1	4	4	4	4	2	1	4
MIL-S-3136, Type I Fuel	1	4	1	2	4	1	1	4	4	4	4	2	1	4
MIL-S-3136, Type II Fuel	2	4	1	4	4	3	2	4	4	4	4	4	2	4
MIL-S-3136, Type III Fuel	2	4	1	4	4	3	2	4	4	4	4	4	2	4
MIL-S-3136, Type IV Oil High Swell	1	4	1	4	4	1	1	4	4	4	4	4	1	2
MIL-S-3136, Type IV Oil Low Swell	1	4	1	1	4	1	1	4	4	4	4	1	1	3
MIL-S-3136, Type V Oil Medium Swell	1	4	1	2	4	1	1	4	4	4	4	2	1	2
MIL-S-81087	1	1	1	1	1	1	1	1	1	1	1	1	2	3
MIL-T-5624, JP-4, JP-5	1	4	1	4	4	2	2	4	4	4	4	4	2	4
MIL-T-83133	1	4	1	3	4	1	1	4	X	X	4	X	2	4
MLO-7277 Hydr.	3	4	1	4	4	3	3	4	4	4	4	4	3	4
MLO-7557	3	4	1	4	4	3	3	4	4	4	4	4	3	4
MLO-8200 Hydr.	2	4	1	1	4	X	1	4	4	4	4	4	2	4
MLO-8515	2	4	1	1	4	3	1	4	4	4	4	3	1	4
Magnesium Chloride	1	1	1	1	1	X	1	1	1	1	1	1	1	1
Magnesium Hydroxide	2	1	1	2	2	4	4	1	2	2	2	1	X	X
Magnesium Salts	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Magnesium Sulphite and Sulphate	1	1	1	1	2	4	X	1	2	2	2	1	1	1
Malathion	2	4	1	X	4	X	X	4	4	4	4	X	2	4
Maleic Acid	4	4	1	4	4	4	X	4	4	4	4	4	X	X
Maleic Anhydride	4	2	4	4	4	4	X	2	4	4	4	4	X	X
Malic Acid	1	2	1	2	2	4	X	4	2	1	3	2	1	2
Mercuric Chloride	1	1	1	1	1	X	X	1	1	1	1	1	X	X
Mercury	1	1	1	1	1	X	X	1	1	1	1	1	X	X
Mercury Vapors	1	1	1	1	1	X	X	1	1	1	1	1	X	X
Mesityl Oxide (Ketone)	4	2	4	4	4	4	4	2	4	4	4	4	4	4
Methane	1	4	1	2	4	1	3	4	4	4	4	2	3	4
Methanol	4	1	4	1	1	4	4	1	1	1	1	1	1	1
Methyl Acetate	4	2	4	2	4	4	4	2	4	4	4	4	4	4
Methyl Acetoacetate	4	2	4	4	X	4	4	2	X	X	X	4	4	2
Methyl Acrylate	4	2	4	2	4	4	4	2	4	4	4	4	4	4
Methyl Alcohol	4	1	4	1	1	4	4	1	1	1	1	1	1	1
Methyl Benzoate	4	4	1	4	4	4	4	4	4	4	4	4	1	4
Methyl Bromide	2	4	1	4	4	3	X	4	4	4	4	4	1	X
Methyl Butyl Ketone	4	1	4	4	4	4	4	1	4	4	4	4	4	4
Methyl Carbonate	4	4	1	4	4	4	4	4	4	4	4	4	2	4

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME



PNEU-DRAULICS 111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	MATERIAL	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Methyl Cellosolve		3	2	4	3	4	4	4	2	4	4	4	2	4	4
Methyl Cellulose		2	2	4	2	2	4	2	2	2	2	2	2	4	2
Methyl Chloride		4	3	1	4	4	4	4	3	4	4	4	4	2	4
Methyl Chloroformate		4	4	1	4	4	4	4	4	4	4	4	4	2	4
Methyl Ether		1	4	1	3	4	4	X	4	1	1	4	4	1	1
Methyl Ethyl Ketone (MEK)		4	1	4	4	4	4	4	1	4	4	4	4	4	4
Methyl Ethyl Ketone Peroxide		4	4	4	4	4	4	4	4	4	4	4	4	4	2
Methyl Formate		4	2	X	2	4	X	X	2	4	4	4	2	X	X
Methyl Isobutyl Ketone (MIBK)		4	3	4	4	4	4	4	3	4	4	4	4	4	4
Methyl Isopropyl Ketone		4	2	4	4	4	4	4	2	4	4	4	4	4	4
Methyl Mercaptan		X	1	X	X	X	X	X	1	X	X	X	X	X	X
Methyl Methacrylate		4	4	4	4	4	4	X	4	4	4	4	4	4	4
Methyl Oleate		4	2	1	4	4	X	X	2	4	X	4	4	2	X
Methyl Salicylate		4	2	X	4	3	X	X	2	X	X	3	4	X	X
Methylacrylic Acid		4	2	3	2	4	4	4	2	4	4	4	4	4	4
Methylcyclopentane		4	4	1	4	4	4	4	4	4	4	4	4	2	4
Methylene Chloride		4	4	2	4	4	4	4	4	4	4	4	4	2	4
Milk		1	1	1	1	1	4	4	1	1	1	1	1	1	1
Mineral Oils		1	3	1	2	4	1	1	3	4	4	4	2	1	2
Mobil SHC 500 Series		3	4	1	2	X	1	2	4	X	X	X	2	2	2
Mobil SHC 600 Series		3	4	1	2	4	1	1	4	X	X	X	2	2	3
Mobilgear 600 Series		3	3	1	1	4	1	2	3	3	4	4	2	1	1
Mobilgear SHC ISO Series		3	3	1	2	4	1	2	3	3	4	4	2	1	1
Mobilgrease HP		2	4	1	2	4	1	1	4	X	4	4	3	1	2
Mobilgrease HTS		2	4	1	2	4	1	1	4	X	4	4	3	1	2
Mobilgrease SM		2	4	1	2	4	1	1	4	X	4	4	3	1	2
Mobilith AW Series		2	4	1	2	4	1	1	4	X	4	4	3	1	2
Mobilith SHC Series		2	4	1	3	4	1	1	4	X	4	4	3	1	2
Mobilmistlube Series		3	3	1	1	4	1	2	3	3	4	4	2	1	1
Mono Bromobenzene		4	4	1	4	4	4	4	4	4	4	4	4	2	4
Mono Ethanolamine		4	2	4	4	2	4	4	2	2	2	2	4	4	2
Monochlorobenzene		4	4	1	4	4	4	4	4	4	4	4	4	2	4
Mononitrotoluene & Dinitrotoluene (40/60 Mixture)		4	4	3	4	4	4	4	4	4	4	4	4	3	4
Monomethyl Hydrazine		2	1	X	2	2	X	X	1	X	X	X	2	X	4
Monomethylaniline		4	2	2	4	4	4	4	2	4	4	4	4	X	X
Monovinyl Acetylene		1	1	1	2	2	X	X	1	2	2	2	2	X	2
Mopar Brake Fluid		3	1	4	2	1	X	X	2	X	X	X	2	4	3
N-Butyl Acetate		4	2	4	4	4	4	4	2	4	4	4	4	4	4
N-Butyl Benzoate		4	1	1	4	2	4	X	1	4	4	4	4	1	X
N-Butyl Butyrate		4	1	1	4	4	4	X	1	4	4	4	4	1	X
N-Butyl Ether		3	3	4	4	4	4	3	3	4	4	4	4	3	4
N-Heptane		1	4	1	2	4	1	2	4	4	4	4	2	3	4
N-Hexaldehyde		4	1	4	1	4	X	2	2	4	4	4	3	4	2
N-Hexane		1	4	1	2	4	1	2	4	4	4	4	2	3	4
N-Hexane-1		2	4	1	2	4	1	2	4	4	4	4	2	4	4
N-Methyl-2-Pyrrolidone		X	2	X	X	X	X	X	X	X	X	X	X	X	X
N-Octane		1	4	1	4	4	4	4	4	4	4	4	4	2	4
N-Pentane		1	4	1	1	3	1	4	4	4	4	4	2	3	4
N-Propyl Acetone		4	1	4	4	4	4	4	1	4	4	4	4	4	4
Naphthalene		4	4	1	4	4	X	2	4	4	4	4	4	1	4
Naphthenic Acid		2	4	1	4	4	X	X	4	4	4	4	4	1	4
Naptha		2	4	1	4	4	2	2	4	4	4	4	4	2	4
Natural Gas		1	4	1	1	2	2	2	4	2	2	2	1	3	4
Neatsfoot Oil		1	2	1	4	4	1	1	2	4	4	4	4	1	2
Neon		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Neville Acid		4	2	1	4	4	4	X	2	4	4	4	4	2	4
Nickel Acetate		2	1	4	2	4	4	4	1	4	1	1	4	4	4
Nickel Chloride		1	1	1	2	1	3	3	1	1	1	1	1	1	1
Nickel Salts		1	1	1	2	1	3	3	1	1	1	1	1	1	1
Nickel Sulfate		1	1	1	1	2	4	3	1	2	2	2	1	1	1
Niter Cake		1	1	1	1	1	4	1	1	1	1	1	1	1	1
Nitric Acid 3 Molar to 158°F		4	2	3	4	3	4	4	2	X	X	X	2	4	4

**NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com**

**SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME**





111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



APPENDIX

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Nitric Acid Concentrated Room Temp.	X	4	2	X	X	X	X	X	X	X	X	X	X	X
Nitric Acid Concentrated to 158°F	4	4	4	4	4	4	4	4	X	X	4	X	4	4
Nitrobenzene	4	1	2	4	4	4	4	1	4	4	4	4	4	4
Nitroethane	4	2	4	2	2	4	4	2	2	2	2	2	4	4
Nitrogen	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Nitrogen Tetroxide (N2O4)	4	4	4	4	4	4	4	2	4	4	4	4	4	4
Nitromethane	4	2	4	3	3	4	4	2	2	2	2	2	4	4
Nitropropane	4	2	4	4	4	4	4	2	4	4	4	4	4	4
Nitrous Oxide	1	1	1	X	X	X	X	X	X	X	X	X	X	1
Noryl GE Phenolic	1	1	X	X	X	X	X	X	X	X	X	X	X	X
Nyvac FR200 Mobil	1	1	1	2	4	X	X	4	4	X	4	3	X	X
O-Chloronaphthalene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
O-Chlorophenol	4	4	1	4	4	4	4	4	4	4	4	4	2	4
O-Dichlorobenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
OS 45 Type III (OS45)	2	4	1	1	4	X	4	4	4	4	4	2	2	4
OS 45 Type IV (OS45-1)	2	4	1	1	4	X	4	4	4	4	4	2	2	4
OS 70	2	4	1	1	4	X	4	4	4	4	4	2	2	4
Octachloro Toluene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Octadecane	1	4	1	2	4	2	1	4	4	4	4	2	1	4
Octyl Alcohol	2	3	1	2	2	4	2	2	2	2	2	2	2	2
Oleic Acid	3	4	2	4	4	4	2	4	4	4	4	4	X	4
Oleum (Fuming Sulfuric Acid)	4	4	1	4	4	4	4	4	4	4	4	4	X	4
Oleum Spirits	2	4	1	3	4	X	3	4	4	4	4	2	2	4
Olive Oil	1	2	1	2	4	1	1	2	4	4	4	2	1	3
Oronite 8200	2	4	1	1	4	X	1	4	4	4	4	4	1	4
Oronite 8515	2	4	1	1	4	X	1	4	4	4	4	4	1	4
Ortho-Dichlorobenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Orthochloro Ethyl Benzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Oxalic Acid	2	1	1	2	2	X	X	1	2	2	2	2	1	2
Oxygen, 200-400°F (Evaluate for specific applications)	4	4	2	4	4	4	4	4	4	4	4	4	4	1
Oxygen, Cold (Evaluate for specific applications)	2	1	1	1	2	2	1	1	2	2	2	1	1	1
Ozone	4	1	1	2	4	2	1	2	4	4	4	1	1	1
P-Cymene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
P-Dichlorobenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
P-Tertiary Butyl Catechol	4	2	1	2	2	4	4	2	2	4	4	2	1	X
PRL-High Temp. Hydr. Oil	2	4	1	2	4	1	2	4	4	4	4	4	1	2
Paint Thinner, Duco	4	4	2	4	4	4	4	4	4	4	4	4	2	4
Palmitic Acid	1	2	1	2	2	X	1	2	2	2	2	3	1	4
Par-al-Ketone	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Para-dichlorobenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Parker O Lube	1	4	1	1	2	1	1	4	4	4	4	1	1	2
Peanut Oil	1	3	1	3	4	1	2	3	4	4	4	2	1	1
Pentane, 2 Methyl	1	4	1	2	4	1	4	4	4	4	4	2	3	4
Pentane, 2-4 dimethyl	1	4	1	2	4	1	4	4	4	4	4	2	3	4
Pentane, 3-Methyl	1	4	1	2	4	1	4	4	4	4	4	2	3	4
Perchloric Acid - 2N	4	2	1	2	4	4	4	2	4	4	4	2	1	4
Perchloroethylene	2	4	1	4	4	4	4	4	4	4	4	4	2	4
Petrolatum	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Petroleum Oil, Above 250°F	4	4	2	4	4	4	4	4	4	4	4	4	4	4
Petroleum Oil, Below 250°F	1	4	1	2	4	2	2	4	4	4	4	2	2	2
Petroleum Oil, Crude	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Phenol	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Phenol, 70%/30% H2O	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Phenol, 85%/15% H2O	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Phenyl Ethyl Ether	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Phenylbenzene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Phenylhydrazine	4	2	1	4	2	4	X	4	2	1	1	4	X	X
Phorone	4	3	4	4	4	4	4	3	4	4	4	4	4	4
Phosphoric Acid 3 Molar to 158°F	1	1	1	2	2	3	4	1	X	X	X	1	2	2
Phosphoric Acid Concentrated Room Temp	2	1	1	2	1	2	4	1	X	X	X	1	3	3
Phosphoric Acid Concentrated to 158°F	4	1	1	3	2	3	4	1	X	X	X	1	3	4
Phosphorous Trichloride	4	1	1	4	4	X	X	1	X	X	4	4	1	X

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME





PNEU-DRAULICS 111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	MATERIAL	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Pickling Solution		4	3	2	4	4	4	4	3	4	4	4	2	4	4
Picric Acid H ₂ O Solution		1	1	1	1	2	X	X	1	2	2	1	1	2	X
Picric Acid Molten		2	2	1	2	2	X	X	2	2	2	2	2	2	4
Pine Oil		1	4	1	4	4	X	X	4	4	4	4	4	1	4
Pinene		2	4	1	3	4	4	2	4	4	4	4	4	1	4
Piperidine		4	4	4	4	4	4	4	4	4	4	4	4	4	4
Plating Solutions Chrome		4	2	1	4	4	4	4	2	4	4	4	4	2	2
Plating Solutions Others		1	1	1	4	4	X	X	1	X	X	4	1	X	4
Pneumatic Service		1	1	1	1	4	4	1	1	4	4	4	1	4	4
Polyvinyl Acetate Emulsion		X	1	X	2	4	X	X	1	X	X	2	2	X	X
Potassium Acetate		2	1	4	2	4	4	4	1	4	1	1	1	4	4
Potassium Chloride		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Potassium Cupro Cyanide		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Potassium Cyanide		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Potassium Dichromate		1	1	1	1	1	1	2	1	1	1	1	1	1	1
Potassium Hydroxide 50%		2	1	4	2	2	4	4	1	2	2	2	1	3	3
Potassium Nitrate		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Potassium Salts		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Potassium Sulfite		1	1	1	1	2	4	1	1	1	2	2	2	1	1
Potassium Sulphate		1	1	1	1	2	4	1	1	1	2	2	2	1	1
Prestone Antifreeze		1	1	1	1	1	4	4	1	1	1	1	1	1	1
Producer Gas		1	4	1	2	4	2	1	4	4	4	4	2	2	2
Propane		1	4	1	2	4	1	3	4	4	4	4	2	2	4
Propyl Acetate		4	2	4	4	4	4	4	2	4	4	4	4	4	4
Propyl Alcohol		1	1	1	1	1	4	4	1	1	1	1	1	1	1
Propyl Nitrate		4	2	4	4	4	4	X	2	4	4	4	4	4	4
Propylene		3	4	1	4	4	4	4	4	4	4	4	4	3	4
Propylene Oxide		4	2	4	4	4	4	4	2	4	4	4	4	4	4
Pydraul, 10E		4	1	4	4	4	4	4	1	4	4	4	4	4	1
Pydraul, 115E		4	1	1	4	4	4	4	1	4	4	4	4	3	4
Pydraul, 230C, 312C, 540C, A200		4	4	1	4	4	4	4	4	4	4	4	4	4	4
Pydraul, 29ELT 30E, 50E, 65E		4	1	1	4	4	4	4	1	4	4	4	4	4	1
Pyranol Transformer Oil		1	4	1	2	4	1	2	4	4	4	4	2	1	4
Pyridine Oil		4	2	4	4	4	4	X	2	4	4	4	4	4	4
Pyrogard 53, Mobil Phosphate Ester		4	1	1	4	4	4	4	1	4	4	4	4	4	4
Pyrogard D, Mobil Water-in-Oil Emulsion		1	4	4	2	4	X	1	4	4	4	4	1	2	3
Pyroligneous Acid		4	2	4	2	4	4	4	2	4	4	4	2	4	X
Pyrolube		4	2	1	4	4	4	4	2	4	4	4	4	2	2
Pyrrrole		4	4	4	4	2	4	X	4	2	2	2	2	2	4
RJ-1 (MIL-F-25558)		1	4	1	2	4	1	1	4	4	4	4	2	1	4
RJ-4 (MIL-F-82522)		2	4	1	4	4	2	2	4	X	X	4	X	1	4
RP-1 (MIL-R-25576)		1	4	1	2	4	1	1	4	4	4	4	2	1	4
Radiation (GAMMA, 1.0 E+07 RADS)		3	2	4	X	X	X	4	4	X	X	4	X	4	2
Rapeseed Oil		2	1	1	2	4	2	2	1	4	4	4	2	1	4
Red Line 100 Oil		1	4	1	2	4	1	1	4	4	4	4	2	1	4
Red Oil (MIL-H-5606)		1	4	1	2	4	1	1	4	4	4	4	2	1	4
SF 1154 GE Silicone Fluid		2	1	1	1	1	1	2	1	X	1	1	1	1	4
SF1147 GE Silicone Fluid		2	3	1	X	X	X	X	3	X	X	X	X	X	4
SF96 GE Silicone Fluid		2	1	1	1	1	1	2	1	1	1	1	1	1	4
SR-10 Fuel		1	4	1	4	4	2	2	4	4	4	4	4	1	4
SR-6 Fuel		2	4	1	4	4	2	2	4	4	4	4	4	1	4
Sal Ammoniac		1	1	1	1	1	1	1	1	1	1	1	1	1	2
Salicylic Acid		2	1	1	X	2	X	X	1	2	1	1	X	1	X
Santo Safe 300		4	3	1	4	4	4	X	3	4	4	4	X	1	1
Sea (Salt) Water		1	1	1	2	1	4	2	1	1	1	1	1	1	1
Sewage		1	1	1	2	1	4	4	1	1	1	1	1	1	1
Shell 3XF Mine Fluid (Fire resist hydr.)		1	4	1	2	4	4	4	4	4	4	4	2	1	X
Shell Alvania Grease #2		1	4	1	2	4	1	1	4	4	4	4	4	1	2
Shell Carnea 19 and 29		1	4	1	4	4	1	2	4	4	4	4	4	1	X
Shell Diala		1	4	1	2	4	1	2	4	4	4	4	4	1	4
Shell Iruis 905		1	4	1	2	4	1	1	4	4	4	4	4	1	4
Shell Lo Hydrax 27 and 29		1	4	1	2	4	1	2	4	4	4	4	4	1	4

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME





111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



APPENDIX

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone	
Shell Macome 72	1	4	1	2	4	1	2	4	4	4	4	4	1	4	
Shell Tellus #32 Pet. Base	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Shell Tellus #68	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Shell UMF (5% Aromatic)	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Silicate Esters	2	4	1	1	4	X	1	4	4	4	4	X	1	4	
Silicone Greases	1	1	1	1	1	1	1	1	1	1	1	1	1	2	3
Silicone Oils	1	1	1	1	1	1	1	1	1	1	1	1	1	3	3
Silver Nitrate	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Sinclair Opaline CX-EP Lube	1	4	1	2	4	1	1	4	4	4	4	2	1	4	
Skelly, Solvent B, C, E	1	4	1	4	4	X	X	4	4	4	4	4	1	X	
Skydrol 500 B4	4	1	4	4	4	4	4	2	4	4	4	4	3	3	
Skydrol LD-4	4	1	4	4	4	4	4	2	4	4	4	4	3	3	
Soap Solutions	1	1	1	2	2	4	4	1	1	1	2	1	1	1	
Socony Mobile Type A	1	4	1	2	4	1	2	4	4	4	4	4	2	4	
Socony Vacuum AMV AC781 (grease)	1	4	1	2	4	1	2	4	4	4	4	4	2	4	
Socony Vacuum PD959B	1	4	1	2	4	1	1	4	4	4	4	2	1	4	
Soda Ash	1	1	1	1	1	X	X	1	1	1	1	1	1	1	
Sodium Acetate	2	1	4	2	4	3	3	1	4	1	1	1	4	4	
Sodium Bicarbonate (Baking Soda)	1	1	1	1	1	X	X	1	1	1	1	1	1	1	
Sodium Bisulfate or Bisulfite	1	1	1	1	2	4	X	1	2	2	1	1	1	1	
Sodium Borate	1	1	1	1	1	X	X	1	1	1	1	1	1	1	
Sodium Carbonate (Soda Ash)	1	1	1	1	1	X	X	1	1	1	1	1	1	1	
Sodium Chloride	1	1	1	1	1	X	1	1	1	1	1	1	X	1	
Sodium Cyanide	1	1	X	1	1	X	X	1	1	1	1	1	X	1	
Sodium Hydroxide, 3 Molar	2	1	2	2	2	4	2	1	1	1	1	1	2	1	
Sodium Hypochlorite	2	1	1	2	2	4	4	1	2	2	2	1	2	2	
Sodium Metaphosphate	1	1	1	2	1	X	X	1	1	1	1	2	1	X	
Sodium Nitrate	2	1	X	2	2	X	X	1	1	1	2	1	X	4	
Sodium Perborate	2	1	1	2	2	X	X	1	2	2	2	2	1	2	
Sodium Peroxide	2	1	1	2	2	4	4	1	2	2	2	2	1	4	
Sodium Phosphate (Dibasic)	1	1	1	2	1	1	1	1	1	1	1	1	X	4	
Sodium Phosphate (Mono)	1	1	1	2	1	1	1	1	1	1	1	1	X	4	
Sodium Phosphate (Tribasic)	1	1	1	2	1	1	1	1	1	1	1	1	X	1	
Sodium Salts	1	1	1	2	1	1	1	1	1	1	1	1	1	1	
Sodium Silicate	1	1	1	1	1	X	X	1	1	1	1	1	X	X	
Sodium Sulphate	1	1	1	1	2	4	1	1	2	2	2	1	1	1	
Sodium Sulphide and Sulfite	1	1	1	1	2	4	1	1	2	2	2	1	1	1	
Sodium Thiosulfate	2	1	1	1	2	4	1	1	2	2	2	1	1	1	
Sour Crude Oil	3	4	1	4	4	4	4	4	4	4	4	X	4	4	
Sour Natural Gas	3	4	1	4	4	4	4	4	4	4	4	X	4	4	
Sovasol No. 1, 2, and 3	1	4	1	2	4	2	2	4	4	4	4	2	1	4	
Sovasol No. 73 and 74	2	4	1	2	4	2	2	4	4	4	4	2	1	4	
Soybean Oil	1	3	1	3	4	1	X	3	4	4	4	3	1	1	
Spray	1	2	1	2	4	1	1	2	4	4	4	4	1	1	
Standard Oil Mobilube GX90-EP Lube	1	4	1	2	4	1	1	4	4	4	4	2	1	4	
Stannic Chloride	1	1	1	4	1	X	X	1	1	1	1	4	1	2	
Stannic Chloride, 50%	1	1	1	4	1	X	X	1	1	1	1	4	1	2	
Stannous Chloride (15%)	1	1	1	1	1	X	X	1	1	1	1	1	1	2	
Stauffer 7700	2	4	1	4	4	2	X	4	4	4	4	4	2	4	
Steam Below 400°F	4	1	4	4	4	4	4	2	4	4	4	4	4	3	
Steam, 400°-500°F	4	3	4	4	4	4	4	4	4	4	4	4	4	4	
Steam, Above 500°F															
Stearic Acid	2	2	X	2	2	X	X	2	2	2	2	2	X	2	
Stoddard Solvent	1	4	1	2	4	1	1	4	4	4	4	4	1	4	
Styrene (Monomer)	4	4	2	4	4	4	X	4	4	4	4	4	3	4	
Sucrose Solutions	1	1	1	2	1	4	4	1	1	1	1	2	1	1	
Sulfur	4	1	1	1	4	4	X	1	4	4	4	X	1	X	
Sulfur Chloride	4	4	1	4	4	4	X	4	4	4	4	4	1	3	
Sulfur Dioxide, Dry	4	1	4	4	2	4	X	2	2	2	2	4	2	2	
Sulfur Dioxide, Liquidified under pressure	4	1	4	4	4	4	X	2	4	4	4	4	2	2	
Sulfur Dioxide, Wet	4	1	4	2	4	4	X	1	4	4	4	3	2	2	
Sulfur Liquors	2	2	1	2	2	4	X	2	2	2	2	2	2	4	

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME





PNEU-DRAULICS 111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Sulfur Molten	4	3	1	3	4	4	4	3	4	4	4	4	3	3
Sulfur Trioxide Dry	4	2	1	4	3	4	X	2	2	2	2	4	2	2
Sulfuric Acid, 3 Molar to 158°F	2	1	1	2	3	2	4	1	X	X	X	1	1	1
Sulfuric Acid, Concentrated Room Temp	X	3	1	X	X	X	3	X	X	X	X	X	X	X
Sulfuric Acid, Concentrated to 158°F	4	4	1	4	4	4	4	4	X	X	X	X	4	4
Sulfurous Acid	2	2	1	2	2	4	3	2	2	2	2	1	X	4
Sunoco #3661	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Sunoco All purpose grease	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Sunoco SAE 10	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Sunsafe (Fire resist. hydr. fluid)	1	4	1	2	4	4	4	4	4	4	4	2	1	X
Super Shell Gas	1	4	1	2	4	2	2	4	4	4	4	4	2	4
Swan Finch EP Lube	1	4	1	4	4	1	1	4	4	4	4	4	1	4
Swan Finch Hypoid-90	1	4	1	2	4	1	1	4	4	4	4	4	1	4
Tannic Acid (10%)	1	1	1	1	2	4	X	1	1	1	1	1	1	2
Tar, bituminous	2	4	1	3	4	4	X	4	4	2	3	4	1	2
Tartaric Acid	1	2	1	2	4	X	1	2	2	1	3	1	1	1
Terpineol	2	3	1	4	4	X	2	3	4	4	4	4	1	X
Tertiary Butyl Alcohol	2	2	1	2	2	4	4	2	2	2	2	2	2	2
Tertiary Butyl Mercaptan	4	4	1	4	4	4	4	4	4	4	4	4	X	4
Tetrabromoethane	4	4	1	4	4	4	X	4	4	4	4	4	2	4
Tetrabutyl Titanate	2	1	1	2	2	X	X	2	2	2	2	4	4	4
Tetrachloroethylene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Tetrachloroethane	4	4	1	4	4	4	4	4	4	4	4	4	2	X
Tetraethyl Lead	2	4	1	2	4	X	X	4	4	4	4	4	2	X
Tetraethyl Lead Blend	2	4	1	4	4	X	X	4	4	4	4	4	2	X
Tetrahydrofuran	4	2	4	4	4	4	3	2	4	4	4	4	4	4
Tetralin	4	4	1	4	4	X	X	4	4	4	4	4	1	4
Texaco 3450 Gear Oil	1	4	1	4	4	1	1	4	4	4	4	4	1	4
Texaco Capella A and AA	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Texaco Meropa 220 (No Lead)	1	4	1	2	4	1	2	4	4	4	4	4	1	4
Texaco Regal B	1	4	1	4	4	1	1	4	4	4	4	4	1	4
Texaco Uni-Temp Grease	1	4	1	2	4	1	1	4	4	4	4	4	1	2
Texamatic A 1581 Fluid	1	4	1	2	4	1	2	4	4	4	4	4	2	4
Texamatic A 3401 Fluid	1	4	1	2	4	1	2	4	4	4	4	4	2	4
Texamatic A 3525 Fluid	1	4	1	2	4	1	2	4	4	4	4	4	2	4
Texamatic A 3528 Fluid	1	4	1	2	4	1	2	4	4	4	4	4	2	4
Texamatic A Transmission Oil	1	4	1	2	4	1	2	4	4	4	4	4	2	4
Texas 1500 Oil	1	4	1	2	4	1	1	4	4	4	4	4	1	2
Therminol 44	4	4	1	4	X	4	X	4	X	X	X	X	X	4
Therminol 55	2	4	1	4	X	2	X	4	X	X	X	X	X	4
Therminol VP-1, 60, 65	4	4	1	4	X	4	X	4	X	X	X	X	X	2
Thiokol TP-90B	4	1	1	2	4	X	X	1	X	X	X	2	2	X
Thiokol TP-95	4	1	1	2	4	X	X	1	X	X	X	2	2	X
Tidewater Multigear, 140 EP Lube	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Tidewater Oil-Beedol	1	4	1	2	4	1	1	4	4	4	4	4	1	2
Titanium Tetrachloride	2	4	1	4	4	4	4	4	4	4	4	4	2	4
Toluene	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Toluene Diisocyanate	4	2	4	4	4	4	X	2	4	4	4	4	4	4
Transformer Oil	1	4	1	2	4	2	1	4	4	4	4	4	1	2
Transmission Fluid Type A	1	4	1	2	4	1	1	4	4	4	4	2	1	2
Triacetin	2	1	4	2	3	4	4	1	2	2	2	2	4	X
Triaryl Phosphate	4	1	1	4	4	4	4	1	4	4	4	4	2	3
Tributoxyethyl Phosphate	4	1	1	4	2	4	4	1	2	4	2	4	2	X
Tributyl Mercaptan	4	4	1	4	4	4	X	4	4	4	4	4	3	4
Tributyl Phosphate	4	1	4	4	4	4	4	2	4	2	2	4	4	4
Trichloroacetic Acid	2	2	3	4	2	4	4	2	2	2	2	4	4	X
Trichloroethane	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Trichloroethylene	3	4	1	4	4	4	4	4	4	4	4	4	2	4
Tricresyl Phosphate	4	1	2	3	2	4	4	1	4	4	4	4	2	3
Triethanol Amine	3	2	4	2	2	4	4	2	2	2	2	2	4	X
Trifluoroethane	4	4	1	4	4	4	4	4	4	4	4	4	2	4
Trinitrotoluene	4	4	2	2	4	4	X	4	4	4	4	2	2	X

**NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com**

**SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME**





111 Brookside Drive • P.O. Box 37
Nicholasville, KY 40340-0037



APPENDIX

FLUID COMPATIBILITY CHART

COMPATIBILITY RATING:
1 = Satisfactory
2 = Fair (Usually OK for Static Seal)
3 = Doubtful (Sometimes OK for Static Seal)
4 = Unsatisfactory
X = Insufficient Data

FLUID NAME	Nitrile	Ethylene Propylene	Fluorocarbon	Neoprene	SBR	Polyacrylate	Polyurethane	Butyl	Butadiene	Isoprene	Natural Rubber	Hypalon	Fluorosilicone	Silicone
Trioctyl Phosphate	4	1	2	4	4	4	4	1	4	4	4	4	2	3
Tripoly Phosphate	4	1	2	3	4	4	4	1	4	4	4	4	1	3
Tung Oil (China Wood Oil)	1	4	1	2	4	X	3	3	4	4	4	3	2	4
Turbine Oil	1	4	1	4	4	1	1	4	4	4	4	4	1	4
Turbine Oil #15 (MIL-L-7808A)	2	4	1	4	4	2	4	4	4	4	4	4	2	4
Turbo Oil #35	1	4	1	2	4	1	1	4	4	4	4	4	1	4
Turpentine	1	4	1	4	4	2	4	4	4	4	4	4	2	4
Type I Fuel (MIL-S-3136)(ASTM Ref. Fuel A)	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Type II Fuel MIL-S-3136	2	4	1	4	4	3	2	4	4	4	4	4	2	4
Type III Fuel MIL-S-3136 (ASTM Ref. Fuel B)	2	4	1	4	4	3	2	4	4	4	4	4	2	4
Ucon Hydrolube J-4	1	1	1	2	1	4	4	1	2	X	X	X	2	1
Ucon Lubricant 50-HB-100	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant 50-HB-260	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant 50-HB-5100	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant 50-HB-660	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant 50-HB55	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant LB-1145	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant LB-135	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant LB-285	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant LB-300X	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant LB-625	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Lubricant LB-65	1	1	1	1	2	X	X	1	2	2	2	2	1	1
Ucon Oil Heat Transfer Fluid 500(Polyalkalene Glycol)	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Oil LB-385	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Ucon Oil LB-400X	1	1	1	1	1	X	X	1	1	1	1	1	1	1
Univis 40 (Hydr. Fluid)	1	4	1	2	4	1	1	4	4	4	4	2	1	4
Univolt #35 (Mineral Oil)	1	4	1	2	4	1	1	4	4	4	4	4	1	4
Unsymmetrical Dimethyl Hydrazine (UDMH)	2	1	4	2	2	X	X	1	1	1	1	1	4	4
Uranium Hexachloride	X	X	1	X	X	X	X	X	X	X	X	X	X	X
VV-H-910	3	1	1	2	1	2	4	2	2	2	2	2	2	2
Varnish	2	4	1	4	4	4	3	4	4	4	4	4	2	4
Vegetable Oil	1	3	1	3	4	1	X	3	4	4	4	X	1	1
Versilube F-50	1	1	1	1	1	1	1	1	1	1	1	1	1	3
Vinegar	2	2	3	2	2	4	4	2	2	2	2	X	3	3
Vinyl Chloride	X	4	X	X	X	X	X	X	X	X	X	X	X	X
Wagner 21B Brake Fluid	3	1	4	2	1	X	X	2	X	X	2	2	4	3
Water	1	1	2	2	1	4	4	1	1	1	1	1	1	1
Wemco C	1	4	1	2	4	1	1	4	4	4	4	4	1	4
Whiskey and Wines	1	1	1	1	1	4	4	1	1	1	1	1	1	1
White Oil	1	4	1	2	4	1	1	4	4	4	4	4	1	4
White Pine Oil	2	4	1	4	4	X	X	4	4	4	4	4	1	4
Wolmar Salt	1	1	1	2	1	2	1	1	1	1	1	1	1	1
Wood Alcohol	1	1	4	1	1	4	4	1	1	1	1	1	1	1
Wood Oil	1	4	1	2	4	1	3	3	4	4	4	3	2	4
Xenon	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Xylene	4	4	1	4	4	4	4	4	4	4	4	4	1	4
Xylenes-Mixed-Aromatic Amines	3	4	4	4	4	4	4	4	4	4	4	4	4	4
Xylol	4	4	1	4	4	4	4	4	4	4	4	4	1	4
Zeolites	1	1	1	1	1	X	X	1	1	1	1	1	1	X
Zinc Acetate	2	1	4	2	4	4	4	1	4	1	1	4	4	4
Zinc Chloride	1	1	1	1	1	4	X	1	1	1	1	1	1	X
Zinc Salts	1	1	1	1	1	4	1	1	1	1	1	1	1	1
Zinc Sulfate	1	1	1	1	2	4	X	1	2	2	2	1	1	1

NATIONWIDE
CALL 1-800-333-SEAL
FAX (859) 887-4165
www.pneu-draulics.com

SALES OFFICE HOURS
7:30 A.M. to 5:30 P.M.
EASTERN STANDARD TIME

